

**CASTING MOLD MANUFACTURING METHOD**


**Patent number:** JP2002336932  
**Publication date:** 2002-11-26  
**Inventor:** KAWAI YOSHIHIDE; SASAKI ATSUSHI  
**Applicant:** DAIDO STEEL CO LTD  
**Classification:**  
- International: **B22C3/00; B22C9/04; B22C3/00; B22C9/04; (IPC1-7):**  
**B22C9/04; B22C3/00**  
- european:  
**Application number:** JP20010145844 20010516  
**Priority number(s):** JP20010145844 20010516

Report a data error here

**Abstract of JP2002336932**

**PROBLEM TO BE SOLVED:** To provide a pattern capable of preventing clogging in a cavity of a primary layer and preventing exposure of one part of a backup layer on the inner side (a pattern side) of the primary layer in a method for manufacturing the pattern for molding a metal of high reactivity at high temperature by a lost wax method.

**SOLUTION:** After forming the primary layer by using a slurry mainly consisting of a refractory of less reactivity at high temperature with the metal on a surface of a wax pattern, a water wet layer is formed on the surface of the primary layer, and the backup layer is formed by using a slurry for reinforcement.



Data supplied from the esp@cenet database - Worldwide

**BEST AVAILABLE COPY**